Q

# Low loss ultra-high laser reflection plane mirror 1450-1650 nm reflectivity 99.99%



## Product Description

PHOTONICS

For applications requiring extremely low-loss coated optics, Xiaoxiao Photonics can provide mirrors with R > 99.995% and total losses less than 10 ppm. Such super-reflective mirrors can be used in ring laser gyroscope components or in cavity ring-down applications. When processing low-absorption, low-scattering coatings on super-polished substrates, we use a modified IBS coater. To ensure cleanliness, such machines are stored in a dedicated ultra-clean room, and all production-related substrate pre-treatment and post-treatment processes are completed in this clean room. In addition, the ultra-clean room is equipped with a variety of measurement equipment, such as white light profilometers and high-resolution microscopes used in the inspection process. The customized cavity ring-down setup can determine the amount of reflection (accuracy can reach four decimal places) and loss. The above values must be determined using a super-polished substrate with a surface roughness of less than < 1 Å rms. In order to ensure the quality of the finished mirror, a white light profilometer is also used for guality inspection



Q



IDEAL THE POWER OF Light PHOTONICS

149595

### • Product features

Low loss, Different sizes can be customized, Incident angle: 0deg

#### • Application area

TDLAS、 Cavity Ring-Down

## • Dimensional Drawing



#### Parameter:

Name 149595 Standard Laser Plane Mir	
Category	Low Loss Optical Devices
Coating material (underside)	137683
Coating material (back side)	140851

### Optical parameters:

Material	Infrasil 302



www.idealphotonics.com

Q

Shape	Round	
Diameter (Ø)	25 mm (-0.1 mm)	
Thickness (t)	6.35 mm (±0.1 mm)	
Parallelism	5 ′	

<b>Optical parameters</b>	Front (S2)	<b>Optical parameters</b>	Back side (S1)
Shape	flat	Shape	flat
Chamfer	0.3 mm (±0.1 mm)	Chamfer	0.3 mm (±0.1 mm)
Test area Øe	21	Test area Øe	21
Surface shape	3/0.2(0.2) [L/10	Surface shape	3/0.2(0.2) [L/10
tolerance	@546.1nm]	tolerance	@546.1nm]
Cleanliness	5/1x0.04; L1x0.004	Cleanliness	5/1x0.04; L1x0.004

Coating Specifications Front (S2) (137683)		
1st working range	Highly reflective(0°,1550nm)>99.99%	
Category	High reflectivity	
Polarization	unpol.	
Incident angle	0°	
Wavelength range	1550 nm	
High reflection	> 99.99 %	
2nd working range	T(0°,1550nm)~0.005%	
Category	Transmittance	
Polarization	unpol.	
Incident angle	0°	
Wavelength range	1550 nm	
HT	~0.005%	
Coating Specifications Backside (S1) (140851)		
1st Operating Range	Anti-reflection(0°,1450-1650nm)<0.2%	
Category	Anti-reflection	
Polarization	unpol.	
Incident Angle	0°	
Wavelength Range	1450-1650 nm	
AR / HT	< 0.2 %	

