

# Raman laser FBG fiber Bragg grating 1240/1270/1484nm



## Product Description

Efficient multi-stage Raman lasers based on phosphosilicate fibers can be created at different wavelengths. The Raman shift of 1330 cm-1 is approximately three times greater than that of Ge doped fibers. The output emission spectra of two cascaded 1.48  $\mu$  m Raman fiber lasers are shown in the figure.

#### Part Number

GTL-FBG-RL-880










### **Parameters**

| FBG Characteristics                                  | GTL-FBG-RL-880                | Tolerance/Notes                    |
|--|-------------------------------|------------------------------------|
| Wavelength Range nm                                  | 1240, 1270, 1484              | $\pm$ 0.1 $^{\sim}$ $\pm$ 1 custom |
| Fiber type   | SM、PM、Double cladding、<br>LMA | Or custom                          |
| Reflectivity, %                                      | 5 ~ 99,9                      | 2 ~ 5 custom                       |
| Bandwidth (FWHM), nm                                 | 0.15~ 1,2                     | custom                             |
| SLSR,dB  | ~8                            | or custom                          |
| FBG pigtail length, m                                | ≥ 0.5                         | or custom                          |
| FBG inscription thought the fiber protective coating | Acrylate, polyimide           | or custom                          |
| FBG Recoating  | None, acrylate, polyimide     | or custom                          |
| Tensile Strength, Kpsi                               | >100                          | or custom                          |
| Optical Connectors                                   | Bare fiber, FC/APC, LC/APC    | or custom                          |




#### Special application fiber Bragg gratings (FBG) include

Wavelength locker FBG
WDM ITU filter 100/200 GHz FBG
Raman laser FBG
Fabry-Perot interferometer FBG
High-temperature resistant fiber Bragg grating
Radiation-resistant FBG

#### The application range of the special FBG series:

External reflector for laser diodes
Filtering optical signals
Optical add/drop multiplexers in WDM systems
Measuring minute temperature or strain changes











Evaluating small vibrations or sound signals Multi-stage Raman lasers High-temperature applications Nuclear industry Aerospace

#### GTL-FBG-WL-810 Wavelength-Locking Fiber Bragg Grating

Used as an external reflector for laser diodes. With the help of these FBGs, it is easy to stabilize the wavelength generation of pump semiconductor lasers and single-frequency lasers. Low-reflection gratings with a Full Width at Half Maximum (FWHM) bandwidth of 0.3 nm to 0.8 nm and a reflectivity of 2% to 5% are ideal for stabilizing pump power in lasers. FBGs with a FWHM bandwidth of around 0.1 nm and a reflectivity of 10% to 20% are placed near the semiconductor laser crystal to create single-frequency sources. FORC Photonics offers wavelength-locking FBGs with highly precise wavelength positions (up to  $\pm$ 0.02 nm).


GTL-FBG-WDM-810 Series WDM ITU Filter 100/200 GHz Fiber Bragg Grating With narrow spectral bandwidth, this FBG is a good element for filtering optical signals. It is widely used as an optical add/drop multiplexer in WDM systems, allowing for high levels of Side-Lobe Suppression Ratio (SLSR) to prevent adjacent channel crosstalk in the system. These FBGs have a flat-top reflection spectrum and steep spectral drop-offs. The non-thermal encapsulation of these FBGs ensures wavelength stability of <0.16 nm in the temperature range from 0 $^{\circ}$  C to +70 $^{\circ}$  C, which is essential for stable operation.

#### GTL-FBG-RL-880 Raman Laser Fiber Bragg Grating

Can be used to create highly efficient multi-stage Raman lasers based on phosphate-silicate fibers at different wavelengths. Compared to germanium-doped fibers, it allows for about three times the Raman shift. For many applications that require very precise measurements of small temperature or strain variations using acoustic waves, paired FBGs can enhance sensitivity.

GTL-FBG-FPI-810 Fabry-Pérot Interferometer Fiber Bragg Grating
This is a pair of FBGs that can detect very small phase shifts. By applying electrically, magnetically, or acoustically enhanced coatings on the fiber between the gratings, extremely small changes in these fields can be measured. For sensing purposes and to assess small vibrations or acoustic signals through interference measurement methods, a low-finesse Fabry-Pérot cavity is typically sufficient.

GTL-FBG-HE-810 High-Environment Fiber Bragg Grating
These FBGs can be provided as separate or different wavelength FBG chains,












enabling multi-point temperature monitoring. Various types of single-mode (SM) fibers and fiber coatings can be used to write these gratings. High-temperature acrylate-coated fibers are suitable for temperatures up to +150° C. Polyimide or metal (copper, aluminum) coated fibers are used for high-temperature applications up to +300° C and +500° C, respectively. With steel tube protection, our high-environment FBGs can be used at temperatures up to  $+700^{\circ}$  C.

GTL-FBG-RH-880 Radiation-Hard Fiber Bragg Grating Written with radiation-hard pure quartz core fibers, this FBG is well-suited for applications in the nuclear industry, aerospace, and other radiation-intensive environments.

The following configurations can be modified according to customer requirements to customize the fiber Bragg grating solution:

| Parameter /PN#  L-810Wav length Locker FBGs  Waveleng | Locker                           | GTL-FBG-WDM-810<br>WDMITU Filter100/<br>200GHzFBGs | GTL-FB<br>G-RL-8<br>80                             | GTL-FBG-FPI<br>-810Fabry-<br>Perot                          | GTL-FB<br>G-HE-8<br>10                             | GTL-FB<br>G-RH-8<br>80   |
|---|----------------------------------|--|--|---|--|--|
|   | Wavelengt<br>h Locker<br>FBGs    |  | Raman<br>LaserF<br>BGs                             | Interferome<br>ter FBGs                                     | HardE<br>nviron<br>ment<br>FBGs                    | Radiati<br>onHard<br>FBGs  |
| Wavelengt<br>h Range<br>[nm]                          | 630-2300                         | 1530-1565 (C-band)<br>or custom<br>1510-1580       | 1240,<br>1270,<br>1484                             | 600-2300  |  | 1000-2<br>300  |
| Quick<br>Order<br>Wavelengt<br>h [nm]]                | 30 values<br>from 633 to<br>2300 | -  | -  | -   | 30<br>values<br>from<br>633 to<br>2300             | -  |
| Fiber Type  | SM, PM,<br>Custom                | SM, Corning SMF-28                                 | SM,<br>PM,<br>Dual-c<br>ore,<br>LMA,<br>Custo<br>m | SM, PM,<br>Dual-core,<br>Radiation-re<br>sistant,<br>Custom | SM,<br>PM,<br>Dual-c<br>ore,<br>LMA,<br>Custo<br>m | SM,<br>PM,<br>Dual-co<br>re,<br>Radiati<br>on-resi<br>stant,<br>Custom |
| Reflectivit<br>y [%]                                  | 2-5,10-20                        | 10-99, Flat-top<br>typical >99.5                   | 5-99.9   | 0.5-99  |  |  |









| Bandwidth                                       |   | 100/200GHzon ITU<br>For                         |         |   |              |         |  |
|---|---|---|---------|---|--------------|---------|--|
| (FWHM)<br>[nm]                                  | 0.3-0.8,0.1-  | 100GHz:@-0.5dB>0.<br>3nm, @-20dB0.65<br>nm      | 0.15-1. | 0.3-0.8   | 0.15-0.<br>8 | 0.3-0.5 |  |
| Distance Between FBGs [mm]                      | -   | -   | -       | 1-200,<br>Custom  | -            | -       |  |
| Channel<br>Isolation<br>[dB]                    | -   | -20   | -       | -   | -            | -       |  |
| Insertion<br>Loss [dB]                          | -   | <0.15   | -       | -   | -            | -       |  |
| Cladding Mode Loss [dB]                         | -   | <0.5 (only for cladding mode suppression fiber) | -       | -   | -            | -       |  |
| Return<br>Loss[dB]                              | ~10   | -   | ~8      | -   | ~8           | ~8      |  |
| FBG pigtail length[m]                           | ≥0.5, custom  |   |         |   |              |         |  |
| FBG Coatin<br>g                                 | None,<br>Acrylic,<br>Polyimide,<br>Aluminum,<br>Copper,<br>Customized | None, Acrylic, Polyimide,<br>Customized         |         | None, Acrylic, Polyimide,<br>Aluminum, Copper,<br>Customized. |              |         |  |
| Tensile Strength [kpsi]                         | >100  | -   | >100    |   |              |         |  |
| Thermal Wavelengt h Stability(0 ° C-+70° C)[nm] | -   | <0.16   | -       | -   | -            | -       |  |
| Optical Connector                               | Bare Fiber, FC/APC, LC/APC, Custom                                    |   |         |   |              |         |  |
| Dimension<br>sLxWxH[m<br>m]                     | -   | 66×18×12  | -       | -   | -            | -       |  |





