

FBG WDM ITU Filter 100/200GHz

Wavelength Division Multiplexing Fiber Bragg Grating



● Product Description


FBGs with narrow spectral bandwidth are excellent components for filtering optical signals. This type of FBG is widely used as an optical add/drop multiplexer in WDM systems. Allow high-level SLSR to avoid adjacent channel crosstalk in the system. The flat top reflection spectrum and steep spectral drop are characteristics of these FBGs. Stable operation requires non thermal encapsulated FBGs with wavelength stability < 0.16 nm within the temperature range of $0-70^{\circ}\text{C}$

● Part Number

GTL-FBG-WDM-810-RS

Parameters

FBG Characteristics	GTL-FBG-WDM-810	Tolerance/Notes
Wavelength Range nm	1530nm-1565nm (C Bands), or custom 1510nm-1580nm	± 0.1
Fiber type	Corning SMF-28	Or custom
Reflectivity, %	10% to 99%, Flat-top typical > 99.5%	2 ÷ 5
Bandwidth (FWHM), nm	100/200 GHz on ITU. For 100GHz: at level -0.5 dB > 0.3 nm and at -20 dB is 0.65 nm	Or custom
Channel spacing, dB	> 20	
Insertion loss, dB	< 0.15	
Cladding mode loss, dB	< 0.5 (for cladding mode suppression fiber only)	or custom
FBG pigtail length	≥ 0.5	or custom
FBG Recoating	None, acrylate, polyimide	or custom
Thermal wavelength stability (0 ÷ +70 °C), nm	< 0.16	
Fiber connector	Bare fiber, FC/APC, LC/APC	or custom
Thermal package, mm	66mm x 18mm x 12mm	



Special application fiber Bragg gratings (FBG) include

Wavelength locker FBG

WDM ITU filter 100/200 GHz FBG

Raman laser FBG

Fabry-Perot interferometer FBG

High-temperature resistant fiber Bragg grating

Radiation-resistant FBG

The application range of the special FBG series:

External reflector for laser diodes

Filtering optical signals
Optical add/drop multiplexers in WDM systems
Measuring minute temperature or strain changes
Evaluating small vibrations or sound signals
Multi-stage Raman lasers
High-temperature applications
Nuclear industry
Aerospace

GTL-FBG-WL-810 Wavelength-Locking Fiber Bragg Grating

Used as an external reflector for laser diodes. With the help of these FBGs, it is easy to stabilize the wavelength generation of pump semiconductor lasers and single-frequency lasers. Low-reflection gratings with a Full Width at Half Maximum (FWHM) bandwidth of 0.3 nm to 0.8 nm and a reflectivity of 2% to 5% are ideal for stabilizing pump power in lasers. FBGs with a FWHM bandwidth of around 0.1 nm and a reflectivity of 10% to 20% are placed near the semiconductor laser crystal to create single-frequency sources. FORC Photonics offers wavelength-locking FBGs with highly precise wavelength positions (up to ± 0.02 nm).

GTL-FBG-WDM-810 Series WDM ITU Filter 100/200 GHz Fiber Bragg Grating

With narrow spectral bandwidth, this FBG is a good element for filtering optical signals. It is widely used as an optical add/drop multiplexer in WDM systems, allowing for high levels of Side-Lobe Suppression Ratio (SLSR) to prevent adjacent channel crosstalk in the system. These FBGs have a flat-top reflection spectrum and steep spectral drop-offs. The non-thermal encapsulation of these FBGs ensures wavelength stability of <0.16 nm in the temperature range from 0°C to $+70^{\circ}\text{C}$, which is essential for stable operation.

GTL-FBG-RL-880 Raman Laser Fiber Bragg Grating

Can be used to create highly efficient multi-stage Raman lasers based on phosphate-silicate fibers at different wavelengths. Compared to germanium-doped fibers, it allows for about three times the Raman shift. For many applications that require very precise measurements of small temperature or strain variations using acoustic waves, paired FBGs can enhance sensitivity.

GTL-FBG-FPI-810 Fabry-Pérot Interferometer Fiber Bragg Grating

This is a pair of FBGs that can detect very small phase shifts. By applying electrically, magnetically, or acoustically enhanced coatings on the fiber between the gratings, extremely small changes in these fields can be measured. For sensing purposes and to assess small vibrations or acoustic signals through interference measurement methods, a low-finesse Fabry-Pérot cavity is typically sufficient.

GTL-FBG-HE-810 High-Environment Fiber Bragg Grating

These FBGs can be provided as separate or different wavelength FBG chains, enabling multi-point temperature monitoring. Various types of single-mode (SM) fibers and fiber coatings can be used to write these gratings. High-temperature acrylate-coated fibers are suitable for temperatures up to +150° C. Polyimide or metal (copper, aluminum) coated fibers are used for high-temperature applications up to +300° C and +500° C, respectively. With steel tube protection, our high-environment FBGs can be used at temperatures up to +700° C.

GTL-FBG-RH-880 Radiation-Hard Fiber Bragg Grating

Written with radiation-hard pure quartz core fibers, this FBG is well-suited for applications in the nuclear industry, aerospace, and other radiation-intensive environments.

The following configurations can be modified according to customer requirements to customize the fiber Bragg grating solution:

Parameter/ PN#	GTL-FB G-WL-8 10 Wavele ngth Loc ker FBGs	GTL-FBG-WDM-810W DMITU Filter100/200G HzFBGs	GTL-FB G-RL-8 80 Raman LaserFB Gs	GTL-FBG-FPI- 810Fabry- P erot Interferomet er FBGs	GTL-FB G-HE-8 10 HardEn vironm ent FBGs	GTL-FBG -RH-880 Radiatio nHardFB Gs
Wavelength Range [nm]	630-2300	1530-1565 (C-band) or custom 1510-1580	124,01 2,701,4 84	600-2300		1000-2300
Quick Order Wavelength [nm]]	30 values from 633 to 2300	-	-	-	30 values from 633 to 2300	-
Fiber Type	SM, PM, Custom	SM, Corning SMF-28	SM, PM, Dual-co re, LMA, Custom	SM, PM, Dual-core, Radiation-res istant, Custom	SM, PM, Dual-co re, LMA, Custom	SM, PM, Dual-cor e, Radiatio n-resista nt, Custom
Reflectivity [%]	2-5,10-20	10-99, Flat-top typical >99.5	5-99.9	0.5-99		
Bandwidth	0.3-0.8,	100/200GHzon ITU For	0.15-1.	0.3-0.8	0.15-0.	0.3-0.5

(FWHM) [nm]	0.1-0.15	100GHz:@-0.5dB>0.3nm, @-20dB0.65 nm	2		8	
Distance Between FBGs [mm]	-	-	-	1-200, Custom	-	-
Channel Isolation [dB]	-	-20	-	-	-	-
Insertion Loss [dB]	-	<0.15	-	-	-	-
Cladding Mode Loss [dB]	-	<0.5 (only for cladding mode suppression fiber)	-	-	-	-
Return Loss[dB]	~10	-	~8	-	~8	~8
FBG pigtail length[m]	≥0.5, custom					
FBG Coating	None, Acrylic, Polyimide, Aluminum, Copper, Customized	None, Acrylic, Polyimide, Customized		None, Acrylic, Polyimide, Aluminum, Copper, Customized.		
Tensile Strength [kpsi]	>100	-	>100			
Thermal Wavelength Stability(0 ° C-+70° C)[nm]	-	<0.16	-	-	-	-
Optical Connector	Bare Fiber, FC/APC, LC/APC, Custom					
Dimensions LxWxH[mm]	-	66×18×12	-	-	-	-